

## LEVANYL® Yellow E4G-A

---

<b>Colour Index</b>	Part I Part II	Pigment Yellow 150
<b>Composition</b>	aqueous, solvent free, organic pigment preparation	
<b>Safety data sheet</b>	145851	
<b>Form supplied</b>	free-flowing paste suitable for pumping and metering	
<b>Shade tolerance (CIElab)</b>	DE max. 1.0	
<b>Color strength tolerance</b>	95.0 – 105.0%	
<b>Density (23 °C)</b>	1.09 – 1.15 g/cm <sup>3</sup>	
<b>Main fields of application</b>	paper pulp, nonwoven	
<b>Further applications</b>	paper coating	
<b>Storage stability</b>	24 months from delivery ex plant LANXESS Deutschland GmbH	
<b>Pigment content</b>	approx. 25 %	
<b>Dispersing agent</b>	anionic	
<b>pH-Value</b>	6.0 – 8.0 form supplied (according to DIN ISO 787-9)	
<b>Viscosity (23 °C)</b>	max. 300 mPa s (D = 70 s <sup>-1</sup> , DIN 53019)	

### Notes on processing:

Always stir before use and close containers after use.

---

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

---



LANXESS Deutschland GmbH  
Business Unit Rhein Chemie Additives  
Kennedyplatz 1  
50569 Cologne, Germany  
<http://rch.lanxess.com>